

DOI: <http://dx.doi.org/10.18265/1517-0306a2021id6262>

ARTIGO ORIGINAL

SUBMETIDO 09/08/2021

APROVADO 04/10/2021


PUBLICADO ON-LINE 11/10/2021

PUBLICADO 30/06/2023

EDITORES ASSOCIADOS


Koje Daniel Vasconcelos Mishina,
Marcelo Cavalcanti Rodrigues, José Carlos
Lima Júnior e Adriano da Silva Marques

Greenhouse gas emissions associated with traditional and alternative concretes

 Mikaelly Renaly
Carlos da Silva ^[1]

 Kalliny dos Santos Gonçalves ^[2]

 Dener Delmiro Martins ^[3]

 Kelly Cristiane
Gomes da Silva ^[4]

 Monica Carvalho ^{[5]*}

[1] mikaely.silva@cear.ufpb.br

[2] kgoncalves@cear.ufpb.br

Programa de Pós-Graduação em
Energias Renováveis, Universidade Federal
da Paraíba (UFPB)

[3] dener.delmiro.martins@academico.ufpb.br

Programa de Pós-Graduação
em Engenharia Mecânica,
Universidade Federal da Paraíba (UFPB)

[4] gomes@cear.ufpb.br

[5] monica@cear.ufpb.br

Departamento de Engenharia de
Energias Renováveis, Universidade
Federal da Paraíba (UFPB)

ABSTRACT: Life Cycle Assessment (LCA) quantifies the environmental impacts associated with products throughout their life cycle. LCA also assists in the interpretation of impact assessment results, enabling improvements in a product or process. This paper applied the LCA methodology to quantify and compare the greenhouse gas emissions associated with different types of concrete: with a traditional binder (Portland cement) and with alkali-activated materials (Metakaolin, Lateritic Soil, and Lateritic Concretion) as precursors. The environmental impact was evaluated using greenhouse gas emissions ($\text{kg CO}_2\text{-eq/m}^3$), considering 1 m^3 of each binder and resistance of approximately 30 MPa, obtained by a recommended mix ratio. The main objective is to evaluate whether alkali-activated binders present lower emissions than Portland cement. The results demonstrated that Portland cement is responsible for over 92% of the emissions associated with traditional concrete production. The use of alternative materials in civil construction, such as laterite soil, reduces carbon dioxide emissions by 79% compared to traditional concrete.

Keywords: alkali-activated materials; concrete; life cycle assessment; Portland cement.

Emissões de gases de efeito estufa associadas a concretos tradicionais e alternativos

RESUMO: A Avaliação de Ciclo de Vida (ACV) é um método que permite quantificar os impactos ambientais de um produto ou processo ao longo do seu ciclo de vida. Ela também auxilia na interpretação dos resultados, com a finalidade de permitir melhorias no produto ou processo. Este artigo aplicou a metodologia em questão para comparar o processo de obtenção do concreto com o ligante tradicional, o cimento Portland, e com materiais alcalinamente ativados tendo como precursores o metacaulim, o solo laterítico e a concreção laterítica. O impacto ambiental foi avaliado por meio das emissões de carbono ($\text{kg CO}_2/\text{m}^3$) considerando 1 m^3 de cada aglomerante, em função do

*Autor para correspondência.

traço recomendado para se obter concreto com resistência de aproximadamente 30 MPa. O objetivo principal deste trabalho foi avaliar se os aglomerantes alcalinamente ativadas apresentam emissões mais baixas do que o cimento Portland. Os resultados demonstraram que o cimento Portland é responsável por mais de 92% das emissões associadas à produção do concreto tradicional. O uso de materiais alternativos na construção civil, como o solo laterítico, reduz as emissões de dióxido de carbono em 79% em comparação ao concreto tradicional.

Palavras-chave: avaliação do ciclo de vida; cimento Portland; concreto; material alcalinamente ativado.

1 Introduction

Energy influences life and all related aspects, is strongly related to the development of countries and civilization, and is very important to ecosystems. Energy demands have been gradually increasing, and concerns about the scarcity of fossil fuels, sustainability, and climate change have motivated the search for renewable energy sources.

Sustainability is correlated to efficiency, time, and durability and is recognized as crucial for reducing pollution levels. Sustainability refers to meeting the needs of humans without compromising the ability to satisfy future generations (NIDHEESH; KUMAR, 2019).

Cement is considered the most consumed material worldwide (GURSEL *et al.*, 2014; STAFFORD *et al.*, 2016) and is widely applied in concrete and mortar composition (SINGH; MIDDENDORF, 2020). The global production of Portland cement was estimated at approximately 4.1 Gt in 2017 (KAN *et al.*, 2019), and its growing demand has increased its production in recent years. China is currently the leading cement producer globally, producing more than 50% of the global volume, corresponding to over 2 million tonnes (NIDHEESH; KUMAR, 2019).

Cement demand estimated for 2050 indicate a need of 0.78-1.36 billion tonnes. The current and future cement demands cause preoccupation due to the energy-intensive character of its products and high requirements of raw materials, in addition to high levels of particulate materials and greenhouse gases. Thus, focusing on different production processes is necessary to reduce emission levels and increase sustainability (NIDHEESH; KUMAR, 2019).

Portland cement concrete contributes to high emissions of greenhouse gases and the depletion of natural resources. Considering all the critical global sustainability challenges, an alternative is the use of alkali-activated cement (MESGARI; AKBARNEZHAD; XIAO, 2020), which is formed by alkaline activation of a precursor, usually supplied as a reactive aluminosilicate powder (SALAS *et al.*, 2018).

The technology of alkali-activated materials points to a positive potential for environmental improvement associated with the civil construction industry when compared to conventional materials (STAFFORD *et al.*, 2016). Glass residues can also be added to cement, decreasing energy demand by 2% and emissions by 2% (SINGH; MIDDENDORF, 2020). This effect is obtained without changing the cement's compressive strength and still achieves a reduction of 20 kg of CO₂-eq when compared to pure Portland cement without additions.

It is estimated that approximately 5%-8% of all carbon emissions related to human activity result from cement and concrete production (KWASNY *et al.*, 2018; NAZARI *et al.*, 2019). In this context, it is essential to carry out a life-cycle analysis of cement and know the environmental impacts caused by its production. The Life Cycle Assessment (LCA) is an analytical tool that assesses the lifetime of materials and their associated ecological performance (BRUIJN *et al.*, 2002), and can contribute to the realization of environmental benefits by indicating the margins for improvement. The sustainability of a product, process, or system can be quantified by identifying hotspots to where improvement efforts should be directed.

This study evaluates the greenhouse gas emissions associated with two binders: traditional (based on Portland cement) and alkali-activated materials, based on Metakaolinite (MK), Lateritic Soil (LS), and Lateritic Concretion with sodium silicate alkaline activator (LC). The mix ratio is based on a resistance of 30 MPa, which enabled the quantification of emissions on a standard basis. A comparison is also made to verify the potential of mitigating climate change. The study is organized as follows: section 2 is the theoretical background, which presents relevant information for the understanding of the context; section 3 is materials and methods, which presents the experimental setup and LCA data; section 4 is results and discussions, which presents the emissions associated with each type of concrete and discusses these results; and finally, section 5 presents the conclusions and suggestions for future research.

2 Theoretical background

Portland cement concrete is one of the most used materials in civil construction worldwide (GOMES *et al.*, 2019). It is composed of aggregates such as gravel, sand, and pulverized material, in addition to a binder (STAFFORD *et al.*, 2016). Portland cement provides high mechanical strength and good durability to the final product (BORGES *et al.*, 2014).

According to the European Standard EN 197-1 (CEN, 2011), Portland cement is formed by clinker and plaster. Clinker is a hydraulic material formed by approximately two-thirds of calcium silicate (in mass) and one-third of Al, Fe, and other compounds. Clinker is obtained after thermal treatment at 1500 °C – this stage involves high emissions of CO₂, which has raised concerns about the sustainability of the clinker productive process (VAN OSS, 2018).

Alkali-activated materials (AAM) are alkaline-activated aluminosilicates of SiO₂ and Al₂O₃ and are synthesized through an alkaline solution. This process is referred to as alkaline synthesis. Several sources can be used as AAM precursors, and among them, metakaolin is the most common (PROVIS; VAN DEVENTER, 2009). The alkaline synthesis results in forming a disordered phase of an alkaline aluminosilicate gel, in which solid precursor particles and the gel pore network are incorporated. These pores contain alkaline activation solutions, normally constituted of sodium silicate, sodium hydroxides, and potassium hydroxides (OLIVEIRA *et al.*, 2019).

Alkali-activated concrete is formed by alkaline liquids, silicon, aluminum, and a geological material or derivative, such as fly ash, blast furnace slag, and rice husk ash. These materials can produce cement binders (MESGARI; AKBARNEZHAD; XIAO, 2020). Alkali-activated concrete relieves the pressure associated with the consumption of natural resources, as it decreases energy use and carbon emissions compared to Portland concrete (BORGES *et al.*, 2014). AAM can be a solution to the

apparent Portland concrete problem, and there has been some research carried out on the durability and mechanical properties of alkali-activated binders (SALAS *et al.*, 2018).

Metakaolin and other industrial by-products used to produce AAM may not be easily accessible due to geographic diversity, leading to economic or environmental unfeasibility. Therefore, it is necessary to analyze the possibility of using materials with lower purity levels, but highly available and naturally occurring, such as clays.

3 Material and methods

The Life Cycle Assessment (LCA) methodology quantifies the potential environmental impacts arising from using different materials and energy forms. LCA has been increasingly used in the development of sustainability-aimed projects and the evaluations of products, processes, or services already in operation (ÇANKAYA; PEKEY, 2019).

LCA addresses the environmental aspects and potential environmental impacts throughout the life cycle of a product, starting from the extraction of raw materials, until its final disposal, including also manufacturing, processing, transportation, use, and maintenance (BRUIJN *et al.*, 2002). LCA is standardized by the International Organization for Standardization, ISO 14040 (ISO, 2006a), and 14044 (ISO, 2006b) standards.

There are four basic phases for an LCA (ISO, 2006a, 2006b): 1) definition of scope and objective (when the functional unit is defined, to which all material and energy flows relate to); 2) inventory analysis (which compiles all material and energy flows, as well as emissions and residues, associated with the functional unit); 3) selection of environmental impact assessment method; and 4) obtainment of results and conclusions.

The software employed herein for the development of the LCA was the Dutch software SimaPro (PRÉ SUSTAINABILITY, 2019), which follows the international ISO standards. The Ecoinvent version 3.5 database (ECOINVENT, 2019) was used to model the processes. Within phase 3, the Intergovernmental Panel on Climate Change method (IPCC, 2013) was used to express the environmental impact, measured in terms of greenhouse gas emissions emitted throughout a time horizon of 100 years.

The same transportation distances were considered for all study cases and were not present in the comparative analysis. This consideration is referred to as a cradle-to-gate assessment (HABERT; LACAILLERIE; ROUSSEL, 2011). The functional unit used for the LCAs was the manufacture of 1 m³ of concrete.

High Early Strength Portland Cement was used to manufacture traditional concrete. For the AAM concretes, MK was used as a standard precursor, and two types of residues (LS and LC) were used as alternative binders. Table 1 presents the chemical composition of the materials, obtained by X-Ray Fluorescence. These lab tests were carried out at the Rapid Solidification Laboratory (Federal University of Paraíba, Northeast Brazil).

Table 1 ►
Chemical composition of
the materials (%).
Source: research data

Sample	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	Na ₂ O	K ₂ O	CaO	MgO	Others
PC	21.16	4.71	1.89	0.39	0.26	68.08	0.48	3.03
MK	64.80	29.74	1.72	0.01	3.10	0.12	0.12	0.39
LS	47.19	15.98	29.66	0.01	0.55	0.68	0.09	5.84
LC	35.58	6.09	56.67	0.19	0.03	0.06	0.00	1.38

Tables 2 and 3 present the traces and inventories for the production of 1 m³ concrete. The Abrams curve was used as a reference to obtain the correct proportion of Portland cement and water, by correlating the w/c factor and strength. The reference value of the w/c ratio adopted herein was 0.45.

Table 2 ▶

Trace and material composition of traditional concrete (density 2,280 kg/m³).
Source: research data

Mix ratio – Portland cement concrete (kg)				
Cement	Sand	Gravel	Plasticizer	w/c*
1	2.59	2.71	1.48%	0.45

Material consumption (kg)				
Cement	Sand	Gravel	Plasticizer	Water
337.00	873.00	913.00	5.00	152.00

* w/c = water/cement factor

Table 3 ▶

Trace and material composition of the AAM-based concretes (density 2,200 kg/m³).
Source: research data

Mix ratio – AAM-based concrete (kg)				
AAM	Sand	Gravel	w/b*	
MK 1	1.40	2.01	1.08	
LS 1	1.40	2.01	1.00	
LC 1	1.40	2.00	1.00	

Material consumption (kg)				
MK	Na₂SiO₃	Sand	Gravel	Water
334.10	82.83	585.00	836.00	362.07
LS	Na₂SiO₃	Sand	Gravel	Water
338.00	83.39	591.00	849.00	338.61
LC	Na₂SiO₃	Sand	Gravel	Water
354.00	65.98	586.00	840.00	354.03

*w/b = water/binder factor (binder may be MK, LS, LC, or PC)

All materials employed were based on a minimum compressive strength of 30 MPa at 28 days, which is an average value indicated for structural purposes according to NBR 8953 (ABNT, 2015). In addition, the choice of concrete strength was based on the construction system used in small-scale buildings in the city of João Pessoa, and the concrete was assumed to be prepared on the construction site.

4 Results and discussion

Table 4 presents the results regarding the greenhouse gas emissions of traditional concrete.

Table 4 ►

Greenhouse gas emissions per 1 m³ of traditional concrete.
Source: research data

Portland cement concrete		
Material	kg CO ₂ -eq	Percentages
Portland cement	306.00	92.72%
Sand	3.69	1.12%
Gravel	9.53	2.89%
Water	0.11	0.03%
Plasticizer	10.70	3.24%
TOTAL	330.03	100.00%

Table 4 evidences the high contribution of Portland cement production, responsible for just over 92% of the emissions associated with concrete production. The major contributor to these emissions is the thermal energy consumed in the clinkerization process, where the chemical calcination reaction of limestone (the most consumed raw material in cement production) occurs, which releases large amounts of CO₂-eq. Limestone is calcinated inside rotary kilns at very high temperatures. Therefore, a possible way to reduce greenhouse emissions is to employ alternative raw materials and replace the fuels employed in the kilns (HOSSAIN *et al.*, 2017).

Table 5 presents the results regarding the greenhouse gas emissions of AAM-based concretes. Lower greenhouse gas emissions were obtained for all AAM-based concrete alternatives, with considerably lower emissions for LS and LC-based concretes (see Table 5). However, there are still margins for improvement within the emissions of AAM-based concrete alternatives (i.e., the potential to further reduce greenhouse gas emissions).

Table 5 ►

Greenhouse gas emissions per 1 m³ of AAM concretes.
Source: research data

AAM MK concrete		
Material	kg CO ₂ -eq	Percentages
MK	78.20	49.16%
Sand	2.48	1.56%
Gravel	8.73	5.49%
Water	0.25	0.16%
Na₂SiO₃	69.40	43.63%
TOTAL	159.06	100.00%

Cont. on next page

AAM LS concrete		
LS	2.56	3.05%
Sand	2.50	2.98%
Gravel	8.87	10.56%
Water	0.24	0.29%
Na ₂ SiO ₃	69.80	83.12%
TOTAL	83.97	100.00%
AAM LC concrete		
LC	2.69	3.87%
Sand	2.48	3.57%
Gravel	8.77	12.62%
Water	0.25	0.36%
Na ₂ SiO ₃	55.30	79.58%
TOTAL	69.49	100.00%

From the analysis of Table 5, it has been demonstrated that alternative binders enable a steep reduction in the global warming potential when compared to traditional concrete: 330 kg CO₂-eq/m³ (conventional concrete) vs. 159.06 kg CO₂-eq/m³ (AAM-based concrete) which represents savings of approximately 52%. The potential for the mitigation of climate change is further enhanced when using AAM LS concrete (which presents a reduction of 75%) and even more when using AAM LC concrete (approximately 79%).

The reductions observed herein are corroborated by other studies, such as Borges *et al.* (2014), where decreases of 72.4% were verified in CO₂ emissions when geopolymer concrete was compared to Portland cement concrete: 271.9 kg CO₂/m³ with Portland cement concrete vs. 75.1 kg CO₂/m³ with geopolymer concrete.

Robayo-Salazar *et al.* (2018) used different precursors to produce AAM with the following proportions: 70% of natural volcanic pozzolan from Colombia and 30% of granulated blast-furnace slag plus NaOH and Na₂SiO as activator solution. The results also confirmed environmental advantages: its carbon footprint was 44.7% smaller than conventional concrete (AAM = 210.90 kg CO₂-eq/m³ versus conventional = 381.17 kg CO₂-eq/m³). According to McLellan *et al.* (2011), there was a 44%-64% reduction in greenhouse gas emissions when using geopolymer concrete – however, the authors highlight that these emissions are highly site-dependent. Salas *et al.* (2018) found a global warming potential (GWP) 64% lower for geopolymer when compared to conventional concrete. Still, these also confirm the dependency on local conditions: sodium hydroxide was produced with local salts, and the electricity mix employed different, low-carbon generating sources. As reported by Meshram and Kumar (2022), in the case of geopolymer cement, most emissions are due to the use of an alkali solution. However, it is still more sustainable than traditional cement and thus has good potential as an alternate binder. The study by Song *et al.* (2016) identified high

emissions associated with producing an alkaline solution with sodium silicate and sodium hydroxide. This demonstrated the potential emission savings that can be realized.

Davidovits (2015) mentions that most published LCAs focus on additional emissions that correspond to long transportation distances for ingredients and chemicals (metakaolin, slag, alkali silicates), which can reach 6000 km for metakaolin or sodium silicate. This could contribute to doubling or even tripling the emission values. Carvalho and Delgado (2017) mentioned that wide variations in emission results can be obtained due to a lack of standardization when using the same methodology to model each inventory. Because the comparison presented herein is on a common basis, with the same database, the comparative assessment is consistent.

Finally, with the progress of industrialization, there is ever-increasing need for cement concrete materials, especially in developing countries. As a result, the amount of Portland cement production increases. It is hoped that the study presented will inspire additional and much-needed research on the environmental issues regarding alkali-activated cement mixtures. The results demonstrated that alkali-activated materials are an environmentally friendly and technically promising alternative to cement.

5 Conclusions

This study used the Life Cycle Assessment methodology to quantify the greenhouse gas emissions of the production of alkaline activated concretes that have Metakaolin, Lateritic Soil, and Lateritic Concretion as precursors, and conventional concrete with Portland cement as a binder.

The results demonstrated that the production of AAM-based concretes presents lower emissions than Portland cement concrete, as the latter emitted 330 kg CO₂-eq/m³ versus 159, 84, and 70 kg CO₂-eq/m³ for alkaline-activated concretes with Metakaolin, Lateritic Soil, and Lateritic Concretion, respectively.

The use of alternative materials decreased greenhouse gas emissions. Alternatives to further decrease emissions include using blast-furnace slag to replace metakaolin in the production of alkaline-activated concretes. Blast-furnace slag can ensure mechanical strength in the early ages of alkaline-activated concretes and reduce the consumption of the activator solution (sodium silicate) because it is less fine than metakaolin and, therefore, requires less solution for the same workability.

There is a growing demand for new building materials with low greenhouse gas emissions associated with their manufacture. Therefore, the studied binders can be widely used as a substitute for Portland cement, but this will only happen when an efficient supply chain for raw materials is available and a distribution network for these products.

Further research can focus on scaling up the Life Cycle Inventory from the laboratory scale to the industrial scale and investigate the effects of AAM on ceramics.

Funding

The authors are grateful for the support of the National Council for Scientific and Technological Development (Research Productivity 307394/2018-2 and development productivity grant 313531/2019-6). Thanks are extended to the Coordination for the Improvement of Higher Education Personnel (CAPES) and the

financial support of grant 046/2021, from the Paraíba State Research Foundation (FAPESQ), for the MSc. scholarships.

Conflicts of interest

The authors declare no conflicts of interest.

References

ABNT –ASSOCIAÇÃO BRASILEIRA DE NORMAS TÉCNICAS (BRAZILIAN ASSOCIATION OF TECHNICAL STANDARDS). **NBR 8953**: Concreto para fins estruturais - Classificação pela massa específica, por grupos de resistência e consistência (Concrete for structural purposes – Classification by specific mass, resistance groups, and consistency). Rio de Janeiro: ABNT, 2015. In Portuguese.

BORGES, P. H. R.; LOURENÇO, T. M. F.; FOUREAUX, A. F. S.; PACHECO, L. S. Estudo comparativo da análise de ciclo de vida de concretos geopoliméricos e de concretos à base de cimento Portland composto (CP II). **Ambiente Construído**, Porto Alegre, v. 14, n. 2, p. 153-168, abr./jun. 2014. DOI: <https://doi.org/10.1590/S1678-86212014000200011>. In Portuguese.

BRUIJN, H.; DUIN, R.; HUIJBREGTS, M. A. J.; GUINEE, J. B.; GORREE, M.; HEIJUNGS, R.; HUPPES, G.; KLEIJN, R.; KONING, A.; OERS, L.; SLEESWIJK, A. W.; SUH, S.; DE HAES, H. A. U. (ed.). **Handbook on Life cycle assessment: an operational guide to the ISO Standards**. Dordrecht: Springer, 2002. DOI: <https://doi.org/10.1007/0-306-48055-7>.

ÇANKAYA, S. PEKEY, B. A comparative life cycle assessment for sustainable cement production in Turkey. **Journal of Environmental Management**, v. 249, 109362, 2019. DOI: <https://doi.org/10.1016/j.jenvman.2019.109362>.

CARVALHO, M.; DELGADO, D. Potential of photovoltaic solar energy to reduce the carbon footprint of the Brazilian electricity matrix. **LALCA: Revista Latino-Americana em Avaliação do Ciclo de Vida**, v. 1, n. 1, p. 64-85, 2017. DOI: <https://doi.org/10.18225/lalca.v1i1.3779>.

CEN – COMITÉ EUROPÉEN DE NORMALISATION. **EN 197-1:2011**. Cement – part 1: composition, specifications, and conformity criteria for common cements. Brussels: Comité Européen de Normalisation (CEN), 2011. Available at: <https://standards.iteh.ai/catalog/standards/cen/64d327b1-d5ac-45e3-8b04-fafec9e0698e/en-197-1-2011>. Accessed on: 18 May 2023.

DAVIDOVITS, J. False values on CO₂ emission for geopolymer cement/concrete published in scientific papers. **Technical Paper**, v. 24, 2015. Available at: http://www.geopolymer.org/fichiers_pdf/False-CO2-values.pdf. Accessed on: 18 May 2023.

ECOINVENT. **Ecoinvent v3.5 Database**. Dübendorf: Swiss Centre for Life Cycle Inventories, 2019. Available at: <http://www.ecoinvent.ch>. Accessed on: 18 May 2023.

GOMES, K. C.; CARVALHO, M.; DINIZ, D. P.; ABRANTES, R. C. C.; BRANCO, M. A.; CARVALHO JUNIOR, P. R. O. Carbon emissions associated with two types of foundations: CP-II Portland cement-based composite vs. geopolymer concrete. **Matéria**, Rio de Janeiro, v. 24, n. 4, e-12525, 2019. DOI: <https://doi.org/10.1590/S1517-707620190004.0850>.

GURSEL, A. P.; MASANET, E.; HORVATH, A.; STADEL, A. Life cycle inventory analysis of concrete production: a critical review. **Cement and Concrete Composites**, v. 51, p. 38-48, 2014. DOI: <https://doi.org/10.1016/j.cemconcomp.2014.03.005>.

HABERT, G.; LACAILLERIE, J. B. E.; ROUSSEL, N. An environmental evaluation of geopolymer based concrete production: reviewing current research trends. **Journal of Cleaner Production**, v. 19, n. 11, p. 1229-1238, 2011. DOI: <https://doi.org/10.1016/j.jclepro.2011.03.012>.

HOSSAIN, M. U.; POON, C. S.; LO, I. M. C.; CHENG, J. C. P. Comparative LCA on using waste materials in the cement industry: a Hong Kong case study. **Resources, Conservation and Recycling**, v. 120, p. 199-208, 2017. DOI: <https://doi.org/10.1016/j.resconrec.2016.12.012>.

IPCC – INTERGOVERNMENTAL PANEL ON CLIMATE CHANGE. **Climate change 2013: The Physical Science Basis**. Cambridge, NY, USA: Cambridge University Press, 2013. 1535 p. Available at: <https://www.ipcc.ch/report/ar5/wg1/>. Accessed on: 18 May 2023.

ISO – INTERNATIONAL ORGANIZATION FOR STANDARDIZATION. **ISO 14040:2006**. Environmental management – Life cycle assessment – Principles and framework. Geneva: International Organization for Standardization (ISO), 2006a. Available at: <https://www.iso.org/standard/37456.html>. Accessed on: 18 May 2023.

ISO – INTERNATIONAL ORGANIZATION FOR STANDARDIZATION. **ISO 14044:2006**. Environmental management – Life cycle assessment – Requirements and guidelines. Geneva: International Organization for Standardization (ISO), 2006b. Available at: <https://www.iso.org/standard/38498.html>. Accessed on: 18 May 2023.

KAN, L.-I.; LVA, J.-W.; DUANA, B.-B.; WU, M. Self-healing of engineered geopolymer composites prepared by fly ash and metakaolin. **Cement and Concrete Research**, v. 125, 105895, 2019. DOI: <https://doi.org/10.1016/j.cemconres.2019.105895>.

KWASNY, J.; SOUTSOS, M. N.; MCINTOSH, J. A.; CLELAND, D. J. Comparison of the effect of mix proportion parameters on behavior of geopolymer and Portland cement mortars. **Construction and Building Materials**, v. 187, p. 635-651, 2018. DOI: <https://doi.org/10.1016/j.conbuildmat.2018.07.165>.

MCLELLAN, B. C.; WILLIAMS, R. P.; LAY, J.; VAN RIESSEN, A.; CORDER, G. D. Costs and carbon emissions for geopolymer pastes in comparison to ordinary portland cement. **Journal of Cleaner Production**, v. 19, n. 9-10, p. 1080-1090, 2011. DOI: <https://doi.org/10.1016/j.jclepro.2011.02.010>.

MESGARI, S.; AKBARNEZHAD, A.; XIAO, J. Z. Recycled geopolymer aggregates as coarse aggregates for Portland cement concrete and geopolymer concrete: effects on

mechanical properties. **Construction and Building Materials**, v. 236, 117571, 2020. DOI: <https://doi.org/10.1016/j.conbuildmat.2019.117571>.

MESHARAM, R. B.; KUMAR, S. Comparative life cycle assessment (LCA) of geopolymer cement manufacturing with Portland cement in Indian context. **International Journal of Environmental Science and Technology**, v. 19, p. 4791-4802, 2022. DOI: <https://doi.org/10.1007/s13762-021-03336-9>.

NAZARI, A.; BAGHERI, A.; SANJAYAN, J. G.; DAO, M.; MALLAWA, C.; ZANNIS, P.; ZUMBO, S. Thermal shock reactions of ordinary Portland cement and geopolymer concrete: microstructural and mechanical investigation. **Construction and Building Materials**, v. 196, p. 492-498, 2019. DOI: <https://doi.org/10.1016/j.conbuildmat.2018.11.098>.

NIDHEESH, P. V.; KUMAR, M. S. An overview of environmental sustainability in cement and steel production. **Journal of Cleaner Production**, v. 231, p. 856-871, 2019. DOI: <https://doi.org/10.1016/j.jclepro.2019.05.251>.

OLIVEIRA, F. A. C.; FERNANDES, J. C.; GALINDO, J.; RODRÍGUEZ, J.; CAÑADAS, I.; VERMELHUDO, V.; NUNES, A.; ROSA, L. G. Portland cement clinker production using concentrated solar energy: a proof-of-concept approach. **Solar Energy**, v. 183, p. 677-688, 2019. DOI: <https://doi.org/10.1016/j.solener.2019.03.064>.

PRÉ SUSTAINABILITY. **SimaPro – Life cycle assessment software**. 2019. Available at: <https://simapro.com/>. Accessed on: 18 May 2023.

PROVIS, J. L.; VAN DEVENTER, J. S. J. Introduction to geopolymers. *In*: PROVIS, J. L.; VAN DEVENTER, S. J. (ed.). **Geopolymers: structure, processing, properties and industrial applications**. Cambridge: Woodhead Publishing, 2009. Cap. 1, p. 1-11. (Woodhead Publishing Series in Civil and Structural Engineering). DOI: <https://doi.org/10.1533/9781845696382.1>.

ROBAYO-SALAZAR, R.; MEJÍA-ARCILA, J.; MEJÍA DE GUTIÉRREZ, R.; MARTÍNEZ, E. Life cycle assessment (LCA) of an alkali-activated binary concrete based on natural volcanic pozzolan: a comparative analysis to OPC concrete. **Construction and Building Materials**, v. 176, p. 103-111, 2018. DOI: <https://doi.org/10.1016/j.conbuildmat.2018.05.017>.

SALAS, D. A.; RAMIREZ, A. D.; ULLOA, N.; BAYKARA, H.; BOERO, A. J. Life cycle assessment of geopolymer concrete. **Construction and Building Materials**, v. 190, p. 170-177, 2018. DOI: <https://doi.org/10.1016/j.conbuildmat.2018.09.123>.

SINGH, N. B.; MIDDENDORF, B. Geopolymers as an alternative to Portland cement: an overview. **Construction and Building Materials**, v. 237, 117455, 2020. DOI: <https://doi.org/10.1016/j.conbuildmat.2019.117455>.

SONG, D.; YANG, J.; CHEN, B.; HAYAT, T.; ALSAEDI, A. Life-cycle environmental impact analysis of a typical cement production chain. **Applied Energy**, v. 164, p. 916-923, 2016. DOI: <https://doi.org/10.1016/j.apenergy.2015.09.003>.

STAFFORD, F. N.; RAUPP-PEREIRA, F.; LABRINCHA, J. A.; HOTZA, D. Life cycle assessment of the production of cement: A Brazilian case study. **Journal**

of Cleaner Production, v. 137, p. 1293-1299, 2016. DOI: <https://doi.org/10.1016/j.jclepro.2016.07.050>.

VAN OSS, H. G. Cement. *In*: U. S. GEOLOGICAL SURVEY. **Mineral commodity summaries 2018**. Reston: U. S. GEOLOGICAL SURVEY, 2018. p. 42-43. DOI: <https://doi.org/10.3133/70194932>.